# **Product information**

# Hypoid Gear Oil (GL5) SAE 80W-90



### **Description**

Mineral low-viscosity hypoid gear oil. For vehicles with tried and tested transmission technology. Even under the most difficult conditions and during large temperature fluctuations, it ensures flawless mechanical component functioning. Provides a stable lubrication film. Provides great lubrication security along with ideal wear protection.

# **Properties**

- excellent resistance to aging
- outstanding viscosity stability
- minimizes wear
- does not attack common sealing materials
- high pressure-absorption capability
- excellent low temperature behavior
- reduces running noise

### Specifications and approvals:

API GL5 • MIL-L 2105 C • MIL-L 2105 D • ZF TE-ML 16B • ZF TE-ML 17B • ZF TE-ML 19B • ZF TE-ML 21A • ZF approval number ZF002053

## LIQUI MOLY also recommends this product for vehicles or assemblies for which the following specifications or original part numbers are required:

MAN 342 Typ M1 • MB 235.0

#### **Technical data**

SAE class (gear oils) 80W-90

SAE J306

Density at 15 °C 0,900 g/cm<sup>3</sup>

DIN 51757

Viscosity at 40 °C 125 mm<sup>2</sup>/s ASTM D 7042-04

14,8 mm<sup>2</sup>/s Viscosity at 100 °C

ASTM D 7042-04

Viscosity at -26°C (Brook- <= 150000 mPas

field)

ASTM D 2983-09

Viscosity index

**DIN ISO 2909** 

Pour point -36 °C

**DIN ISO 3016** 

204 °C Flash point

**DIN ISO 2592** 

Color number (ASTM) L 2.5

**DIN ISO 2049** 

# Areas of application

For heavy-duty motor vehicle transmissions, particularly axle drives with hypoid gearing.

### **Application**

During selection, keep to the viscosity class stipulated by the transmission manufacturer. Miscible with all branded gear oils. Fully effective only when used alone. Only use in manual transmissions for which API GL 5 oils are stipulated.

#### Available pack sizes

4406 1 l Can plastic

D-GB-I-E-P

1 l Can plastic 3924

D-RUS-UA

20 l Canister plastic 1048

D-GB-I-E-P

60 l Drum sheet metal 3592

D-GB

205 l Drum sheet metal 1049

D-GB

Our information is based on thorough research and may be considered reliable, although not legally binding.